

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representation of  
The original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT).

(51) International Patent Classification n <sup>6</sup> : A61L 25/00, 15/28	A1	(11) International Publication Number: WO 97/41900
		(43) International Publication Date: 13 November 1997 (13.11.97)

(21) International Application Number: PCT/GB97/01244  
(22) International Filing Date: 8 May 1997 (08.05.97)  
(30) Priority Data:  
9609474.3 8 May 1996 (08.05.96) GB

(71) Applicant (for all designated States except US): INNOVATIVE TECHNOLOGIES LIMITED [GB/GB]; Road Three, Winsford Industrial Estate, Winsford, Cheshire CW7 3PD (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): GILDING, Denis, Keith [GB/GB]; Nepenthe, Winsford Road, Wettehall, Winsford, Cheshire CW7 4DL (GB). QIN, Yimin [CN/GB]; 123 Victoria Road, Northwich, Cheshire CW9 5RQ (GB).

(74) Agent: ATKINSON, Peter, Birch; Marks & Clerk, Sussex House, 83-85 Mosley Street, Manchester M2 3LG (GB).

(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).

Published

With international search report.  
Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(54) Title: HYDROGELS

(57) Abstract

A method of producing a hydrogel product comprises impregnating a coherent fibrous structure with an aqueous solution of a hydrogel precursor material, said fibres incorporating cations which are capable of cross-linking said precursor material to form a fibre reinforced hydrogel as the hydrogel product.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## HYDROGELS

The present invention relates to hydrogels, i.e. cross-linked macromolecular networks which are swollen with water or biological fluids. The invention relates more particularly, but not exclusively, to such hydrogels that are useful as wound dressings.

A hydrogel is a cross-linked macromolecular network swollen with water or biological fluids. It is known that hydrogels are useful as wound dressings, particularly because of their ability to donate fluid to a wound to maintain a moist "healing environment". There are however disadvantages with prior art hydrogel dressings (e.g. Clearsite) in that they can be weak and difficult to handle.

It is therefore an object of the present invention to obviate or mitigate the above disadvantages.

According to a first aspect of the present invention there is provided a method of producing a hydrogel product comprising impregnating a coherent fibrous structure (preferably sterilised) with an aqueous solution of a hydrogel precursor material (preferably sterilised), said fibres incorporating cations which are capable of cross-linking said precursor material to form a fibre reinforced hydrogel as the hydrogel product.

By "coherent fibrous structure" we mean that the fibrous structure is comprised of fibres which are positively held together to maintain the overall coherency of the structure although obviously we do not preclude the possibility that individual fibres of the structure may become loose and detached. Such structures are to be distinguished from, for example, loose chopped fibres in which there is no mechanical forces holding the fibres together into the form of a structure. Examples of coherent fibrous structures which may be used in accordance with the invention are knitted, woven, and non-woven products such as felts, matts and the like. A preferred fibrous structure is a non-woven felt.

A particularly preferred fibrous structure is a non-woven felt made of calcium alginate fibres and having a basis weight of 30 to 200 gsm, more preferably 40 to 80 gsm, and most preferably about 60 gsm.

The method of the invention is effected by impregnating the fibrous structure with the solution of hydrogel precursor, preferably in ratio (by weight) of solution: fabric of (20-70):1. The method results in the production of a hydrogel which has been cross-linked (i.e. "set") by ions released from the fibres. In the final hydrogel the fibrous structure provides, in effect, a reinforcement giving strength for easy handling of the hydrogel. If desired the hydrogel product may be autoclaved.

Hydrogels produced in accordance with the invention may be in the form of sheets typically having a thickness of 1 mm to 10 mm.

The hydrogels are in a hydrated form and are capable of donating moisture to a wound. The hydrogels may be used for treating superficial wounds with low to medium levels of exudates

Examples of hydrogel precursor material which may be used include sodium alginate, sodium carboxymethyl cellulose, sodium pectinate, sodium O-carboxymethyl chitosan (OCC), sodium N,O-carboxymethyl chitosan (NOCC), sodium polyacrylate, and naturally occurring gums and synthetic polymers containing pendant carboxylic acid groups (humectants).

The hydrogel precursor may consist wholly or partially of Ace Mannan (or other component of Aloe Vera) which is a natural polymer known to accelerate healing of wounds. The Ace Mannan may, for example, provide up to 80% of the matrix. The Ace Mannan may be clinical grade material obtainable from Carrington Laboratories, Dallas, Texas, U.S.A.

The hydrogel precursor may, if desired, incorporate an agent to stimulate the healing of wounds. Examples of such agents include growth factors, e.g. whey growth factor extract (obtainable from GroPep Ltd. Australia) or Precatide copper acetate complex (obtainable from Procyte, U.S.A.).

The fibres which are used contain a di- or higher valent cation which is effective for cross-linking the hydrogel. Examples of suitable cations include  $\text{Ca}^{2+}$ ,

$\text{Zn}^{2+}$ , and cations which also act as enzyme cofactors. Particular preferred examples of fibres which may be used are calcium alginate fibres.

Preferably the hydrogel precursor solution incorporates a bacteriostatic agent, preferably propylene glycol.

In a preferred method of carrying out the invention, the hydrogel precursor (e.g. an alginate) is dissolved in a mixture of 75%-85% by weight water and 15% to 25% by weight propylene glycol. The resultant solution is then used to impregnate the coherent fibrous structure to form the hydrogel.

It is possible for the hydrogel precursor solution and coherent fibrous structure to be supplied separately whereby the method of the first aspect of the invention may be effected in, for example, a surgery. This affords the possibility of either using the coherent fibrous structure as a dressing per se or using it to produce a hydrogel product as discussed above.

Therefore according to a second aspect of the invention there is provided a kit of parts for producing a hydrogel product, the kit comprising a container of a hydrogel precursor solution (preferably sterilised) and a coherent fibrous structure (preferably sterilised).

Hydrogel products obtained in accordance with the invention may be used in conjunction with hydrophilic films which have an increased breathability in the presence of liquid water as compared to moisture vapour alone. The use of such a film over the hydrogel (i.e. on the side remote from the wound) ensures that water is vented from the hydrogel through the film. Therefore the dissolution of the hydrogel may be controlled.

Typically the breathable film will be of a material which, as a 50 micron film, has an MVTR in the presence of moisture vapour alone of 6,000 to 10,000  $\text{g m}^{-2} 24\text{hr}^{-1}$  as measured by ASTM E96B and an MVTR in the presence of a liquid water (as measured by ASTM E96BW) of 6,000 to 10,000  $\text{g m}^{-2} 24\text{hr}^{-1}$ . Typically the breathable film will have a thickness of 30-70 microns, more preferably 40-60 microns, e.g. about 50 microns.

The breathable film may for example be of polyurethane. Suitable films are available from Innovative Technologies Limited under the designations IT325, IT425 and IT625.

The invention is illustrated with reference to the following non-limiting Example.

#### Example

A non-woven felt made of calcium alginate MP1-2A felt, available from Innovative Technologies) having a weight/unit area of about  $60 \text{ g/m}^2$  was treated with a 2% alginate (Protanol LF 10/60, ex-Pronava) dissolved in a 80/20 mixture of water and propylene glycol. The ratio of solution to felt was 40 to 1. The solution was first spread out in a flat stainless steel dish having a size of about 30 cm x 30 cm and the felt was then placed in solution. The fibres interacted with the sodium alginate in the solution to form a sheet hydrogel. The resultant gel could be autoclaved to provide a hydrated sheet hydrogel for treating superficial wounds with low to medium level of exudate.



**CLAIMS**

1. A method of producing a hydrogel product comprising impregnating a coherent fibrous structure with an aqueous solution of a hydrogel precursor material, said fibres incorporating cations which are capable of cross-linking said precursor material to form a fibre reinforced hydrogel as the hydrogel product.
2. A method as claimed in claim 1 wherein the coherent fibre structure is a knitted, woven or non-woven product.
3. A method as claimed in claim 2 wherein the coherent fibre structure is a felt or matt.
4. A method as claimed in any one of claims 1 to 3 wherein the hydrogel precursor is sodium alginate, sodium carboxymethyl cellulose, sodium pectinate, sodium O-carboxymethyl chitosan (OCC), sodium N,O-carboxymethyl chitosan (NOCC), sodium polyacrylate, and naturally occurring gums and synthetic polymers containing pendant carboxylic acid groups (humectants).
5. A method as claimed in any one of claims 1 to 3 wherein the hydrogel precursor consists wholly or partially of Ace Mannan (or other component of Alloc Vera).
6. A method as claimed in any one of claims 1 to 5 wherein the hydrogel precursor incorporates an agent to stimulate the healing of wounds.
7. A method as claimed in any one of claims 1 to 6 wherein said cations are  $\text{Ca}^{2+}$ ,  $\text{Zn}^{2+}$  and/or cations which also act as enzyme cofactors.

8. A method as claimed in any one of the preceding claims wherein the fibres are calcium alginate fibres.
9. A method as claimed in any one of the preceding claims wherein the hydrogel precursor is dissolved in a mixture of 75% to 85% by weight water and 15% to 25% by weight propylene glycol.
10. A method as claimed in any one of the preceding claims wherein the ratio by volume of the hydrogel precursor solution to the coherent fibre structure is (20 to 70):1.
11. A hydrogel product which comprises a hydrogel and a reinforcement of a fibrous structure which is coherent per se.
12. A hydrogel product as produced by the method of any one of claims 1 to 10 or as claimed in claim 11 for use as a primary wound dressing for superficial wounds with low to medium levels of exudate.
13. A kit of parts for producing a hydrogel product, the kit comprising a container of a hydrogel precursor solution (preferably sterilised) and a coherent fibrous structure (preferably sterilised).

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB.97/01244

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A61L25/00 A61L15/28

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 96 10106 A (INNOVATIVE TECH LTD ;QIN YIMIN (GB); GILDING KEITH DENNIS (GB)) 4 April 1996 see claims; examples 1-3 ---	1-13
P,X	WO 97 03710 A (INNOVATIVE TECH LTD ;GILDING DENNIS KEITH (GB); QIN YIMIN (GB)) 6 February 1997 see claims; examples 1,2 ---	1-13
P,X	WO 96 13285 A (INNOVATIVE TECH LTD ;QIN YIMIN (GB); GILDING KEITH DENNIS (GB)) 9 May 1996 see claims; examples ---	1-13
Y	WO 89 12471 A (BRITCAIR LTD) 28 December 1989 see claims ---	1-13
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

1 October 1997

Date of mailing of the international search report

06-10-1997

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

ESPINOSA, M

# INTERNATIONAL SEARCH REPORT

In<sup>t</sup>ernational Application No  
PCT/GB 97/01244

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 90 14110 A (VILAIN JEAN) 29 November 1990 see claims ---	1-13
P,Y	WO 96 13282 A (INNOVATIVE TECH LTD ;QIN YIMIN (GB); GILDING KEITH DENNIS (GB)) 9 May 1996 see the whole document ---	1-13
A	EP 0 666 081 A (SQUIBB BRISTOL MYERS CO) 9 August 1995 see claims ---	1-13
A	WO 95 19795 A (SQUIBB BRISTOL MYERS CO ;LYDON MICHAEL JAMES (GB); QUEEN DOUGLAS ()) 27 July 1995 ---	
A	GB 2 221 620 A (JOHNSON & JOHNSON PATIENT CARE) 14 February 1990 -----	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 97/01244

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9610106 A	04-04-96	AU 3530695 A EP 0783605 A GB 2307687 A	19-04-96 16-07-97 04-06-97
WO 9703710 A	06-02-97	AU 6525296 A	18-02-97
WO 9613285 A	09-05-96	AU 3750495 A EP 0788380 A GB 2308846 A	23-05-96 13-08-97 09-07-97
WO 8912471 A	28-12-89	AU 3854089 A	12-01-90
WO 9014110 A	29-11-90	AU 5561690 A EP 0472575 A JP 4505267 T	18-12-90 04-03-92 17-09-92
WO 9613282 A	09-05-96	AU 3706695 A EP 0788378 A GB 2309909 A	23-05-96 13-08-97 13-08-97
EP 0666081 A	09-08-95	CA 2140827 A	25-07-95
WO 9519795 A	27-07-95	AU 1667395 A CA 2179415 A EP 0740554 A FI 962916 A NO 962316 A	08-08-95 27-07-95 06-11-96 19-07-96 03-07-96
GB 2221620 A	14-02-90	AU 634164 B AU 3897389 A IE 63408 B JP 3009761 A NL 8901936 A	18-02-93 01-02-90 19-04-95 17-01-91 16-02-90

**THIS PAGE BLANK (USPTO)**